

Kernmaster



Kernmaster is a static-rappelling line constructed with a traditional “mantle” sleeve consisting of 48 strands of polyester. The inside, or “kern,” is a braided core of energy-absorbing nylon. The core is fully steam-stabilized to enhance the rope’s flexibility and prevent hardening in service.


The braid also bends more easily and with less fatiguing of the core when cycled over sheaves or dropped over a parapet. The sleeve is either white with red tracers or solution-cast fiber (color added prior to yarn production), which makes for lasting colors and enhanced wear resistance.

Standards: 11 mm, 13 mm: CE0120 EN1891 Type A

Diameter Inches	Diameter mm	Weight Lbs/100ft	Weight Kg/100m	Average Spliced Break Strength* Lbs	Average Spliced Break Strength* Kg	Minimum Spliced Break Strength* Lbs	Minimum Spliced Break Strength* Kg	Maximum** Work Load 5:1 Lbs	Maximum** Work Load 5:1 Kg
3/8	10	4.0	6.0	3,250	1,475	2,925	1,328	325	148
7/16	11	5.5	8.2	7,300	3,310	6,570	2,979	730	331
1/2	13	7.6	11.3	8,800	3,995	7,920	3,596	880	400
5/8	16	11.4	17.0	11,000	4,990	9,900	4,491	1,100	499

* Knots and abrupt bends significantly reduce the strength of all ropes and lower maximum working load.

** Working load is based on static or moderately dynamic lifting/pulling operations. Instantaneous changes in load, up or down, in excess or 10% of the rope’s related working load constitute hazardous shock load and would void the normal working-load recommendation. Consult Yale Cordage for guidelines for working loads and the safe use of rope.



Energy Absorption

The colored area under the curve represents the rope’s energy-absorption capability.

- Green working 622 ft. lbs./lb.
- Red ultimate 9,775 ft. lbs./lb.

Dielectric Strength: The maximum allowable leakage for clean, dry Kernmaster is 500 micro-amperes when tested at 100kV per Yale Method 712-1701 Rev 1 “Routine Production Test.” Absorbed and entrained moisture or impurities will increase rope’s conductivity dramatically.

- Maximum Working Load
- Minimum Break Strength
- Average Break Strength

Specific Gravity: 1.23