

Nylon Brait

Plaited 8-Strand




Nylon Brait combines braiding technology with plaited rope optimizing the best of both rope styles. Nylon Brait's most outstanding feature is its high energy absorption, which comes from a combination of the very long yarn path and stranditure developed especially to maximize energy absorption.

Nylon Brait can absorb (or mitigate) greater amounts of dynamic energy than 3-stranded or braided rope structures with less damage. Brait's energy absorption also keeps the corresponding loads on attachment points smaller since the rope does more work internally. Brait is easily spliced and the spliced rope delivers 100% of the ropes advertised strength.

Diameter (in)	Weight (lbs/100ft)	Avg Spliced Break Strength* (lbs)	Min Spliced Break Strength* (lbs)	Maximum Working Load 5:1 ** (Lbs)
3/8	3.8	4,000	3,600	800
1/2	6.1	8,300	7,470	1,660
17/32	6.4	9,200	8,280	1,840
5/8	9.4	12,200	10,980	2,440
21/32	9.6	12,900	11,610	2,580
11/16	11	15,000	13,500	3,000
3/4	14	17,000	15,300	3,400
7/8	19	22,000	19,800	4,400
1	23.7	27,000	24,300	5,400
1-1/8	30.5	34,750	31,275	6,950
1-1/4	35.6	40,500	36,450	8,100
1-1/2	49.8	56,700	51,030	11,340
1-5/8	59.5	67,700	60,930	13,540
1-3/4	74	84,700	76,230	16,940

*Knots and abrupt bends significantly reduce the strength of all ropes and lower maximum working load.

**Working load is based on static or moderately dynamic lifting/ pulling operations. Instantaneous changes in load, up or down, in excess of 10% of the rope's rated working load constitute hazardous shock load and would void the normal working-load recommendation. Consult Yale Cordage for guidelines for working loads and the safe use of rope.



Energy Absorption

The colored area under the curve represents the rope's ability to do "work" and is expressed in foot-pounds per pound of rope in tension.

- Green working 1,426 ft. lbs./lb.
- Red ultimate 23,680 ft. lbs./lb.

Approved Splice Technique: #10017302.

Minimum Break Strength

Specific Gravity: 1.14